

Requested Patent: EP1084726A2

Title: METERED DOSE INHALER FOR FLUTICASONE PROPIONATE ;

Abstracted Patent: EP1084726 ;

Publication Date: 2001-03-21 ;

Inventor(s):

ASHURST IAN C (US); LI LI (US); HERMAN CRAIG S (US); RIEBE MICHAEL T (US) ;

Applicant(s): GLAXO WELLCOME INC (US) ;

Application Number: EP20000128067 19960410 ;

Priority Number(s):

EP19960910810 19960410; US19950422111 19950414; US19960584859 19960105 ;

IPC Classification: A61M15/00 ;

Equivalents: EP1166811, A3, SI820322T ;

ABSTRACT:

A metered dose inhaler having part or all of its internal surfaces coated with one or more fluorocarbon polymers, optionally in combination with one or more non-fluorocarbon polymers, for dispensing an inhalation drug formulation comprising fluticasone propionate, or a physiologically acceptable solvate thereof, and a fluorocarbon propellant optionally in combination with one or more other pharmacologically active agents or one or more excipients.

(19)



Eur päisches Patentamt
European Patent Office
Office eur péen des brevets



(11)

EP 1 084 726 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
21.03.2001 Bulletin 2001/12

(51) Int Cl.7: **A61M 15/00**

(21) Application number: **00128067.6**

(22) Date of filing: **10.04.1996**

(84) Designated Contracting States:
**AT BE CH DE DK ES FI FR GB GR IE IT LI LU MC
NL PT SE**

Designated Extension States:
AL LT LV SI

(30) Priority: **14.04.1995 US 422111**
05.01.1996 US 584859

(62) Document number(s) of the earlier application(s) in
accordance with Art. 76 EPC:
96910810.9 / 0 820 322

(71) Applicant: **GLAXO WELLCOME INC.**
Research Triangle Park,
North Carolina 27709 (US)

(72) Inventors:
• **Ashurst, Ian C.**
Research Triangle Park, NC 27709 (US)

- **Herman, Craig S**
Research Triangle Park, NC 27709 (US)
- **LI, LI**
Research Triangle Park, NC 27709 (US)
- **Riebe, Michael T.**
Research Triangle Park, NC 27709 (US)

(74) Representative: **Pike, Christopher Gerard et al**
Pike & Co.
Hayes Loft
68A Hayes Place
Marlow, Bucks. SL7 2BT (GB)

Remarks:

This application was filed on 21 - 12 - 2000 as a
divisional application to the application mentioned
under INID code 62.

(54) **Metered dose inhaler for fluticasone propionate**

(57) A metered dose inhaler having part or all of its
internal surfaces coated with one or more fluorocarbon
polymers, optionally in combination with one or more
non-fluorocarbon polymers, for dispensing an inhalation

drug formulation comprising fluticasone propionate, or
a physiologically acceptable solvate thereof, and a fluor-
ocarbon propellant optionally in combination with one or
more other pharmacologically active agents or one or
more excipients.

EP 1 084 726 A2

Description

BACKGROUND OF THE INVENTION

[0001] Drugs for treating respiratory and nasal disorders are frequently administered in aerosol formulations through the mouth or nose. One widely used method for dispensing such aerosol drug formulations involves making a suspension formulation of the drug as a finely divided powder in a liquefied gas known as a propellant. The suspension is stored in a sealed container capable of withstanding the pressure required to maintain the propellant as a liquid. The suspension is dispersed by activation of a dose metering valve affixed to the container.

[0002] A metering valve may be designed to consistently release a fixed, predetermined mass of the drug formulation upon each activation. As the suspension is forced from the container through the dose metering valve by the high vapor pressure of the propellant, the propellant rapidly vaporizes leaving a fast moving cloud of very fine particles of the drug formulation. This cloud of particles is directed into the nose or mouth of the patient by a channelling device such as a cylinder or open-ended cone. Concurrently with the activation of the aerosol dose metering valve, the patient inhales the drug particles into the lungs or nasal cavity. Systems of dispensing drugs in this way are known as "metered dose inhalers" (MDI's). See Peter Byron, Respiratory Drug Delivery, CRC Press, Boca Raton, FL (1990) for a general background on this form of therapy.

[0003] Patients often rely on medication delivered by MDI's for rapid treatment of respiratory disorders which are debilitating and in some cases, even life threatening. Therefore, it is essential that the prescribed dose of aerosol medication delivered to the patient consistently meet the specifications claimed by the manufacturer and comply with the requirements of the FDA and other regulatory authorities. That is, every dose in the can must be the same within close tolerances.

[0004] Some aerosol drugs tend to adhere to the inner surfaces, i.e., walls of the can, valves, and caps, of the MDI. This can lead to the patient getting significantly less than the prescribed amount of drug upon each activation of the MDI. The problem is particularly acute with hydrofluoroalkane (also known as simply "fluorocarbon") propellant systems, e.g., P134a and P227, under development in recent years to replace chlorofluorocarbons such as P11, P114 and P12.

[0005] We have found that coating the interior can surfaces of MDI's with a fluorocarbon polymer significantly reduces or essentially eliminates the problem of adhesion or deposition of fluticasone propionate on the can walls and thus ensures consistent delivery of medication in aerosol from the MDI.

SUMMARY OF THE INVENTION

[0006] A metered dose inhaler having part or all of its internal surfaces coated with one or more fluorocarbon polymers, optionally in combination with one or more non-fluorocarbon polymers, for dispensing an inhalation drug formulation comprising fluticasone propionate, or a physiologically acceptable solvate thereof, and a fluorocarbon propellant optionally in combination with one or more other pharmacologically active agents or one or more excipients.

DETAILED DESCRIPTION OF THE INVENTION

[0007] The term "metered dose inhaler" or "MDI" means a unit comprising a can, a crimped cap covering the mouth of the can, and a drug metering valve situated in the cap, while the term "MDI system" also includes a suitable channelling device. The terms "MDI can" means the container without the cap and valve. The term "drug metering valve" or "MDI valve" refers to a valve and its associated mechanisms which delivers a predetermined amount of drug formulation from an MDI upon each activation. The channelling device may comprise, for example, an actuating device for the valve and a cylindrical or cone-like passage through which medicament may be delivered from the filled MDI can via the MDI valve to the nose or mouth of a patient, e.g. a mouthpiece actuator. The relation of the parts of a typical MDI is illustrated in US Patent 5,261,538 incorporated herein by reference.

[0008] The term "fluorocarbon polymers" means a polymer in which one or more of the hydrogen atoms of the hydrocarbon chain have been replaced by fluorine atoms. Thus, "fluorocarbon polymers" include perfluorocarbon, hydrofluorocarbon, chlorofluorocarbon, hydrochlorofluorocarbon polymers or other halogen substituted derivatives thereof. The "fluorocarbon polymers" may be branched, homo-polymers or co-polymers.

[0009] U.S. Patent No. 4,335,121, incorporated herein by reference, teaches an antiinflammatory steroid compound known by the chemical name [(6a, 11b, 16a, 17a)-6, 9-difluoro-11-hydroxy-16-methyl-3-oxo-17-(1-oxopropoxy) androsta-1, 4-diene-17-carbothioic acid, S-fluoromethyl ester and the generic name "fluticasone propionate". Fluticasone propionate in aerosol form, has been accepted by the medical community as useful in the treatment of asthma and is marketed under the trademarks "Flovent" and "Flonase". Fluticasone propionate may also be used in the form of a physiologically acceptable solvate.

[0010] The term "drug formulation" means fluticasone propionate (or a physiologically acceptable solvate thereof) optionally in combination with one or more other pharmacologically active agents such as other antiinflammatory agents, analgesic agents or other respiratory drugs and optionally containing one or more excipients, and a fluorocarbon propellant. The term "excipi-

ents" as used herein means chemical agents having little or no pharmacological activity (for the quantities used) but which enhance the drug formulation or the performance of the MDI system. For example, excipients include but are not limited to surfactants, preservatives, flavorings, antioxidants, antiaggregating agents, and cosolvents, e.g., ethanol and diethyl ether.

[0011] Suitable surfactants are generally known in the art, for example, those surfactants disclosed in European Patent Application No. 0327777. The amount of surfactant employed is desirably in the range of 0.0001% to 50% weight to weight ratio relative to the drug, in particular 0.05 to 5% weight to weight ratio. A particularly useful surfactant is 1,2-di[7-(F-hexyl) hexanoyl]-glycero-3-phospho-N,N,N-trimethylethanolamine also known as 3, 5, 9-trioxa-4-phosphadocosan-1-aminium, 17, 17, 18, 18, 19, 19, 20, 20, 21, 21, 22, 22, 22-tridecafluoro-7-[(8, 8, 9, 9, 10, 10, 11, 11, 12, 12, 13, 13, 13-tridecafluoro-1-oxotridecyl)oxy]-4-hydroxy-N, N,N-trimethyl-10-oxo-, inner salt, 4-oxide.

[0012] A polar cosolvent such as C₂₋₆ aliphatic alcohols and polyols e.g. ethanol, isopropanol and propylene glycol, preferably ethanol, may be included in the drug formulation in the desired amount, either as the only excipient or in addition to other excipients such as surfactants. Suitably, the drug formulation may contain 0.01 to 5% w/w based on the propellant of a polar cosolvent e.g. ethanol, preferably 0.1 to 5% w/w e.g. about 0.1 to 1% w/w.

[0013] It will be appreciated by those skilled in the art that the drug formulation for use in the invention may, if desired, contain fluticasone propionate (or a physiologically acceptable solvate thereof) in combination with one or more other pharmacologically active agents. Such medicaments may be selected from any suitable drug useful in inhalation therapy. Appropriate medicaments may thus be selected from, for example, analgesics, e.g. codeine, dihydromorphine, ergotamine, fentanyl or morphine; aniginal preparations, e.g. diltiazem; antiallergics, e.g. cromoglycate, ketotifen or nedocromil; anti-infectives e.g. cephalosporins, penicillins, streptomycin, sulphonamides, tetracyclines and pentamidine; antihistamines, e.g. methapyrilene; anti-inflammatories, e.g. beclomethasone (e.g. the dipropionate), flunisolide, budesonide, tipredane or triamcinolone acetone; anti-tussives, e.g. noscapine; bronchodilators, e.g. salbutamol, salmeterol, ephedrine, adrenaline, fenoterol, formoterol, isoprenaline, metaproterenol, phenylephrine, phenylpropanolamine, pirbuterol, reproterol, rimiterol, terbutaline, isoetharine, tulobuterol, orciprenaline, or (-)-4-amino-3,5-dichloro- α -{[6-[2-(2-pyridinyl)ethoxy]hexyl]amino}methyl]benzenemethanol; diuretics, e.g. amiloride; anticholinergics e.g. ipratropium, atropine or oxitropium; hormones, e.g. cortisone, hydrocortisone or prednisolone; xanthines e.g. aminophylline, choline theophyllinate, lysine theophyllinate or theophylline; and therapeutic proteins and peptides, e.g. insulin or glucagon. It will be clear to a person skilled in the art that,

where appropriate, the medicaments may be used in the form of salts (e.g. as alkali metal or amine salts or as acid addition salts) or as esters (e.g. lower alkyl esters) or as solvates (e.g. hydrates) to optimise the activity and/or stability of the medicament and/or to minimise the solubility of the medicament in the propellant.

[0014] Particularly preferred drug formulations contain fluticasone propionate (or a physiologically acceptable solvate thereof) in combination with a bronchodilator such as salbutamol (e.g. as the free base or the sulphate salt) or salmeterol (e.g. as the xinafoate salt).

[0015] A particularly preferred drug combination is fluticasone propionate and salmeterol xinafoate.

[0016] "Propellants" used herein mean pharmacologically inert liquids with boiling points from about room temperature (25°C) to about -25°C which singly or in combination exert a high vapor pressure at room temperature. Upon activation of the MDI system, the high vapor pressure of the propellant in the MDI forces a metered amount of drug formulation out through the metering valve then the propellant very rapidly vaporizes dispersing the drug particles. The propellants used in the present invention are low boiling fluorocarbons; in particular, 1,1,1,2-tetrafluoroethane also known as "propellant 134a" or "P 134a" and 1,1,1,2,3,3,3-heptafluoro-n-propane also known as "propellant 227" or "P 227".

[0017] Drug formulations for use in the invention may be free or substantially free of formulation excipients e.g. surfactants and cosolvents etc. Such drug formulations are advantageous since they may be substantially taste and odour free, less irritant and less toxic than excipient-containing formulations. Thus, a preferred drug formulation consists essentially of fluticasone propionate, or a physiologically acceptable salt thereof, optionally in combination with one or more other pharmacologically active agents particularly salmeterol (e.g. in the form of the xinafoate salt), and a fluorocarbon propellant. Preferred propellants are 1,1,1,2-tetrafluoroethane, 1,1,1,2,3,3,3-heptafluoro-n-propane or mixtures thereof, and especially 1,1,1,2-tetrafluoroethane.

[0018] Further drug formulations for use in the invention may be free or substantially free of surfactant. Thus, a further preferred drug formulation comprises or consists essentially of albuterol (or a physiologically acceptable salt thereof), optionally in combination with one or more other pharmacologically active agents, a fluorocarbon propellant and 0.01 to 5% w/w based on the propellant of a polar cosolvent, which formulation is substantially free of surfactant. Preferred propellants are 1,1,1,2-tetrafluoroethane, 1,1,1,2,3,3,3-heptafluoro-n-propane or mixtures thereof, and especially 1,1,1,2-tetrafluoroethane or 1,1,1,2,3,3,3-heptafluoro-n-propane.

[0019] Most often the MDI can and cap are made of aluminum or an alloy of aluminum, although other metals not affected by the drug formulation, such as stainless steel, an alloy of copper or tin plate, may be used. An MDI can may also be fabricated from glass or plastic.

Preferably, however, the MDI cans employed in the present invention are made of aluminium or an alloy thereof. Advantageously, strengthened aluminium or aluminum alloy MDI cans may be employed. Such strengthened MDI cans are capable of withstanding particularly stressful coating and curing conditions, e.g. particularly high temperatures, which may be required for certain fluorocarbon polymers. Strengthened MDI cans which have a reduced tendency to malform under high temperatures include MDI cans comprising side walls and a base of increased thickness and MDI cans comprising a substantially ellipsoidal base (which increases the angle between the side walls and the base of the can), rather than the hemispherical base of standard MDI cans. MDI cans having an ellipsoidal base offer the further advantage of facilitating the coating process.

[0020] The drug metering valve consists of parts usually made of stainless steel, a pharmacologically inert and propellant resistant polymer, such as acetal, polyamide (e.g., Nylon®), polycarbonate, polyester, fluorocarbon polymer (e.g., Teflon®) or a combination of these materials. Additionally, seals and "O" rings of various materials (e.g., nitrile rubbers, polyurethane, acetyl resin, fluorocarbon polymers), or other elastomeric materials are employed in and around the valve.

[0021] Fluorocarbon polymers for use in the invention include fluorocarbon polymers which are made of multiples of one or more of the following monomeric units: tetrafluoroethylene (PTFE), fluorinated ethylene propylene (FEP), perfluoroalkoxyalkane (PFA), ethylene tetrafluoroethylene (ETFE), vinylidene fluoride (PVDF), and chlorinated ethylene tetrafluoroethylene. Fluorinated polymers which have a relatively high ratio of fluorine to carbon, such as perfluorocarbon polymers e.g. PTFE, PFA, and FEP, are preferred.

[0022] The fluorinated polymer may be blended with non-fluorinated polymers such as polyamides, polyimides, polyethersulfones, polyphenylene sulfides and amineformaldehyde thermosetting resins. These added polymers improve adhesion of the polymer coating to the can walls. Preferred polymer blends are PTFE/FEP/polyamideimide, PTFE/polyethersulphone (PES) and FEP-benzoguanamine.

[0023] Particularly preferred coatings are pure PFA, FEP and blends of PTFE and polyethersulphone (PES).

[0024] Fluorocarbon polymers are marketed under trademarks such as Teflon®, Tefzel®, Halar®, Hostafion®, Polyflon® and Neoflon®. Grades of polymer include FEP DuPont 856-200, PFA DuPont 857-200, PTFE-PES DuPont 3200-100, PTFE-FEP-polyamideimide DuPont 856P23485, FEP powder DuPont 532, and PFA Hoechst 6900n. The coating thickness is in the range of about 1µm to about 1mm. Suitably the coating thickness is in the range of about 1µm to about 100µm, e.g. 1µm to 25µm. Coatings may be applied in one or more coats.

[0025] Preferably the fluorocarbon polymers for use in the invention are coated onto MDI cans made of metal, especially MDI cans made of aluminium or an alloy

thereof.

[0026] The particle size of the particular (e.g., micronised) drug should be such as to permit inhalation of substantially all the drug into the lungs upon administration of the aerosol formulation and will thus be less than 100 microns, desirably less than 20 microns, and, in particular, in the range of 1-10 microns, e.g., 1-5 microns.

[0027] The final drug formulation desirably contains 0.005-10% weight to weight ratio, in particular 0.005-5% weight to weight ratio, especially 0.01-1.0% weight to weight ratio, of drug relative to the total weight of the formulation.

[0028] A further aspect of the present invention is a metered dose inhaler having part or all of its internal metallic surfaces coated with one or more fluorocarbon polymers, optionally in combination with one or more non-fluorocarbon polymers, for dispersing an inhalation drug formulation comprising fluticasone propionate and a fluorocarbon propellant optionally in combination with one or more other pharmacologically active agents and one or more excipients.

[0029] A particular aspect of the present invention is an MDI having part or essentially all of its internal metallic surfaces coated with PFA or FEP, or blended fluoropolymer resin systems such as PTFE-PES with or without a primer coat of a polyamideimide or polyethersulphone for dispensing a drug formulation as defined hereinabove. Preferred drug formulations for use in this MDI consist essentially of fluticasone propionate (or a physiologically acceptable solvate, thereof), optionally in combination with one or more other pharmacologically active agents particularly salmeterol (e.g. in the form of the xinafoate salt), and a fluorocarbon propellant, particularly 1,1,1,2-tetrafluoroethane, 1,1,1,2,3,3,3-heptafluoropropane or mixtures thereof, and especially 1,1,1,2-tetrafluoroethane. Preferably the MDI can is made of aluminium or an alloy thereof.

[0030] The MDI can may be coated by the means known in the art of metal coating. For example, a metal, such as aluminum or stainless steel, may be precoated as coil stock and cured before being stamped or drawn into the can shape. This method is well suited to high volume production for two reasons. First, the art of coating coil stock is well developed and several manufacturers can custom coat metal coil stock to high standards of uniformity and in a wide range of thicknesses. Second, the precoated stock can be stamped or drawn at high speeds and precision by essentially the same methods used to draw or stamp uncoated stock.

[0031] Other techniques for obtaining coated cans is by electrostatic dry powder coating or by spraying preformed MDI cans inside with formulations of the coating fluorinated polymer/polymer blend and then curing. The preformed MDI cans may also be dipped in the fluorocarbon polymer/polymer blend coating formulation and cured, thus becoming coated on the inside and out. The fluorocarbon polymer/polymer blend formulation may also be poured inside the MDI cans then drained out

leaving the insides with the polymer coat.

[0032] Conveniently, for ease of manufacture, pre-formed MDI cans are spray-coated with the fluorinated polymer/polymer blend.

[0033] The fluorocarbon polymer/polymer blend may also be formed in situ at the can walls using plasma polymerization of the fluorocarbon monomers. Fluorocarbon polymer film may be blown inside the MDI cans to form bags. A variety of fluorocarbon polymers such as ETFE, FEP, and PTFE are available as film stock.

[0034] The appropriate curing temperature is dependent on the fluorocarbon polymer/polymer blend chosen for the coating and the coating method employed. However, for coil coating and spray coating temperatures in excess of the melting point of the polymer are typically required, for example, about 50°C above the melting point, for up to about 20 minutes such as about 5 to 10 minutes eg about 8 minutes or as required. For the above named preferred and particularly preferred fluorocarbon polymer/polymer blends curing temperatures in the range of about 300°C to about 400°C, e.g. about 350°C to 380°C are suitable for plasma polymerization typically temperatures in the range of about 20°C to about 100°C may be employed.

[0035] The MDI's taught herein may be prepared by methods of the art (e.g., see Byron, above and U.S. patent 5,345,980) substituting conventional cans for those coated with a fluorinated polymer/polymer blend. That is, fluticasone propionate and other components of the formulation are filled into an aerosol can coated with a fluorinated polymer/polymer blend. The can is fitted with a cap assembly which is crimped in place. The suspension of the drug in the fluorocarbon propellant in liquid form may be introduced through the metering valve as taught in U.S. 5,345,980 incorporated herein by reference.

[0036] The MDI's with fluorocarbon polymer/polymer blend coated interiors taught herein may be used in medical practice in a similar manner as non-coated MDI's now in clinical use. However the MDI's taught herein are particularly useful for containing and dispensing inhaled drug formulations with hydrofluoroalkane-fluorocarbon propellants such as 134a with little, or essentially no, excipient and which tend to deposit or cling to the interior walls and parts of the MDI system. In certain cases it is advantageous to dispense an inhalation drug with essentially no excipient, e.g., where the patient may be allergic to an excipient or the drug reacts with an excipient.

[0037] MDI's containing the formulations described hereinabove, MDI systems and the use of such MDI systems for the treatment of respiratory disorders e.g. asthma comprise further aspects of the present invention.

[0038] It will be apparent to those skilled in the art that modifications to the invention described herein can readily be made without departing from the spirit of the invention. Protection is sought for all the subject matter described herein including any such modifications.

[0039] The following non-limitative Examples serve to illustrate the invention.

EXAMPLES

Example 1

[0040] Standard 12.5 mL MDI cans (Presspart Inc., Cary, NC) were spray-coated (Livingstone Coatings, Charlotte, NC) with primer (DuPont 851-204) and cured to the vendor's standard procedure, then further spray-coated with either FEP or PFA (DuPont 856-200 and 857-200, respectively) and cured according to the vendor's standard procedure. The thickness of the coating is approximately 10µm to 50µm. These cans are then purged of air (see PCT application number WO94/22722 (PCT/EP94/00921)), the valves crimped in place, and a suspension of about 20 mg fluticasone propionate in about 12 gm P134a is filled through the valve.

Example 2

[0041] Standard 0.46 mm thick aluminum sheet (United Aluminum) was spray-coated (DuPont, Wilmington, DE) with FEP (DuPont 856-200) and cured. This sheet was then deep-drawn into cans (Presspart Inc., Cary, NC). The thickness of the coating is approximately 10µm to 50µm. These cans are then purged of air, the valves crimped in place, and a suspension of about 40 mg fluticasone propionate in about 12 gm P134A is filled through the valve.

Example 3

[0042] Standard 12.5 ml MDI cans (Presspart Inc., Cary NC) are spray-coated with PTFE-PES blend (DuPont) as a single coat and cured according to the vendor's standard procedure. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air, the valves crimped in place, and a suspension of about 41.0mg, 21.0mg, 8.8mg or 4.4mg micronised fluticasone propionate in about 12g P134a is filled through the valve.

Example 4

[0043] Standard 12.5ml MDI cans (Presspart Inc., Cary NC) are spray-coated with PTFE-FEP-polyamide-imide blend (DuPont) and cured according to the vendor's standard procedure. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air the valves crimped in place, and a suspension of about 41.0mg, 21.0mg, 8.8mg or 4.4mg micronised fluticasone propionate in about 12g P134a is filled through the valve.

Example 5

[0044] Standard 12.5ml MDI cans (Presspart Inc., Cary NC) are spray-coated with FEP powder (DuPont FEP 532) using an electrostatic gun. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air, the valves crimped in place, and a suspension of about 41.0mg, 21.0mg, 8.8mg or 4.4mg micronised fluticasone propionate in about 12g P134a was filled through the valve.

Example 6

[0045] Standard 0.46mm thick aluminium sheet is spray coated with FEP-Benzoguanamine and cured. This sheet is then deep-drawn into cans. These cans are then purged of air, the valves crimped in place, and a suspension of about 41.0mg, 21.0mg, 8.8mg, or 4.4mg micronised fluticasone propionate in about 12g P134a is filled through the valve.

Example 7

[0046] Standard 12.5 ml MDI cans (Presspart Inc., Cary NC) are spray-coated with an aqueous dispersion of PFA (Hoechst PFA-6900n) and cured. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air, the valves crimped in place, and a suspension of about 41.0mg, 21.0mg, 8.8mg, or 4.4mg micronised fluticasone propionate in about 12g P134a is filled through the valve.

Example 8

[0047] Standard 12.5 ml MDI cans (Presspart Inc., Cary NC) are spray-coated with PTFE-PES blend (DuPont) as a single coat and cured according to the vendor's standard procedure. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air, the valves crimped in place, and a suspension of about 8.8mg, 22mg or 44mg of micronised fluticasone propionate with about 6.4mg micronised salmeterol xinafoate in about 12g P134a is filled through the valve.

Example 9

[0048] Standard 12.5ml MDI cans (Presspart Inc., Cary NC) are spray-coated with PTFE-FEP-polyamide-imide blend (DuPont) and cured according to the vendor's standard procedure. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air the valves crimped in place, and a suspension of about 8.8mg, 22mg or 44mg of micronised fluticasone propionate with about 6.4mg micronised salmeterol xinafoate in about

12g P134a is filled through the valve.

Example 10

[0049] Standard 12.5ml MDI cans (Presspart Inc., Cary NC) are spray-coated with FEP powder (DuPont FEP 532) using an electrostatic gun. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air, the valves crimped in place, and a suspension of about 8.8mg, 22mg or 44mg of micronised fluticasone propionate with about 6.4mg micronised salmeterol xinafoate in about 12g P134a is filled through the valve.

Example 11

[0050] Standard 0.46mm thick aluminium sheet is spray coated with FEP-Benzoguanamine and cured. This sheet is then deep-drawn into cans. These cans are then purged of air, the valves crimped in place, and a suspension of about 8.8mg, 22mg or 44mg of micronised fluticasone propionate with about 6.4mg micronised salmeterol xinafoate in about 12g P134a is filled through the valve.

Example 12

[0051] Standard 12.5 ml MDI cans (Presspart Inc., Cary NC) are spray-coated with an aqueous dispersion of PFA (Hoechst PFA-6900n) and cured. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air, the valves crimped in place, and a suspension of about 8.8mg, 22mg or 44mg of micronised fluticasone propionate with about 6.4mg micronised salmeterol xinafoate in about 12g P134a is filled through the valve.

Example 13

[0052] Standard 12.5 ml MDI cans (Presspart Inc., Cary NC) are spray-coated with PTFE-PES blend (DuPont) as a single coat and cured according to the vendor's standard procedure. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air, the valves crimped in place, and a suspension of about 5.5mg, 13.8mg or 27.5mg micronised fluticasone propionate with about 4mg micronised salmeterol xinafoate in about 8g P134a is filled through the valve.

Example 14

[0053] Standard 12.5ml MDI cans (Presspart Inc., Cary NC) are spray-coated with PTFE-FEP-polyamide-imide blend (DuPont) and cured according to the vendor's standard procedure. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air the valves

crimped in place, and a suspension of about 5.5mg, 13.8mg or 27.5mg micronised fluticasone propionate with about 4mg micronised salmeterol xinafoate in about 8g P134a is filled through the valve.

Example 15

[0054] Standard 12.5ml MDI cans (Presspart Inc., Cary NC) are spray-coated with FEP powder (DuPont FEP 532) using an electrostatic gun. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air, the valves crimped in place, and a suspension of about 5.5mg, 13.8mg or 27.5mg micronised fluticasone propionate with about 4mg micronised salmeterol xinafoate in about 8g P134a is filled through the valve.

Example 16

[0055] Standard 0.46mm thick aluminium sheet is spray coated with FEP-Benzoguanamine and cured. This sheet is then deep-drawn into cans. These cans are then purged of air, the valves crimped in place, and a suspension of about 5.5mg, 13.8mg or 27.5mg micronised fluticasone propionate with about 4mg micronised salmeterol xinafoate in about 8g P134a is filled through the valve.

Example 17

[0056] Standard 12.5 ml MDI cans (Presspart Inc., Cary NC) are spray-coated with an aqueous dispersion of PFA (Hoechst PFA-6900n) and cured. The thickness of the coating is between approximately 1µm and approximately 20µm. These cans are then purged of air, the valves crimped in place, and a suspension of about 5.5mg, 13.8mg or 27.5mg micronised fluticasone propionate with about 4mg micronised salmeterol xinafoate in about 8g P134a is filled through the valve.

Examples 18-22

[0057] Examples 3 to 7 are repeated except that a suspension of about 13.3mg micronised fluticasone propionate in about 21.4g P227 is filled through the valve.

Examples 23-27

[0058] Examples 3 to 7 are repeated except that 66mg, or 6.6mg micronised fluticasone propionate in about 182mg ethanol and about 18.2g P134a is filled through the valve.

Examples 28-52

[0059] Examples 3 to 27 are repeated except that modified 12.5ml MDI cans having a substantially ellipsoidal base (Presspart Inc., Cary NC) were used.

[0060] Dose delivery from the MDIs tested under simulated use conditions is found to be constant, compared to control MDIs filled into uncoated cans which exhibit a significant decrease in dose delivered through use.

Claims

1. A metering valve for dispensing an inhalation drug aerosol formulation having part or all of its internal surfaces coated with one or more fluorocarbon polymers, optionally in combination with one or more non-fluorocarbon polymers.
2. A metering valve according to claim 1 wherein said fluorocarbon polymer is a perfluorocarbon polymer.
3. A metering valve according to either of claims 1 and 2 wherein said fluorocarbon polymer is selected from the group consisting of PTFE, PFA, FEP and mixtures thereof.
4. A metering valve according to any one of claims 1 to 3, wherein said fluorocarbon polymer is in combination with a non-fluorocarbon polymer selected from the group consisting of polyamideimide, polyethersulphone and mixtures thereof.
5. A metering valve according to any of claims 1 to 4 wherein said one or more fluorocarbon polymers are applied by a plasma polymerisation process.
6. A metering valve according to any of claims 1 to 5 comprising a metal wherein part or all of the internal metallic surfaces are coated.
7. A metering valve according to claim 6 wherein the metal is selected from the group consisting of stainless steel, aluminium or an alloy thereof.
8. A metering valve according to any of claims 1 to 7 comprising a pharmacologically inert and propellant resistant polymer.
9. A metering valve according to claim 8 wherein said pharmacologically inert and propellant resistant polymer is selected from the group consisting of acetal, polyamide, polycarbonate, polyester, fluorocarbon polymer and any combinations thereof.
10. A metering valve according to any of claims 1 to 9 additionally comprising a seal.
11. A metering valve according to claim 10 wherein said seal is composed of a material selected from the group consisting of nitrile rubbers, polyurethane, acetyl resin, fluorocarbon polymers, or other elastomeric materials.

12. A metering valve according to any of claims 1 to 11 containing said drug formulation.
13. A metering valve according to Claim 12, wherein said drug formulation comprises fluticasone propionate or a physiologically acceptable solvate thereof in combination with one or more other pharmacologically active agents.
14. A metering valve according to Claim 13, wherein said drug formulation comprises fluticasone propionate or a physiologically acceptable solvate thereof in combination with a bronchodilator or an antiallergic.
15. A metering valve according to Claim 14, wherein said drug formulation comprises fluticasone propionate or a physiologically acceptable solvate thereof in combination with a drug selected from the group consisting of salmeterol xinafoate, salbutamol or a physiologically acceptable solvate thereof.
16. A metering valve according to any of claims 12 to 15 wherein said drug formulation additionally comprises a fluorocarbon propellant.
17. A metering valve according to Claim 16, wherein said fluorocarbon propellant is selected from the group consisting of 1,1,1,2-tetrafluoroethane, 1,1,1,2,3,3,3-heptafluoro-n-propane or mixtures thereof.
18. A metering valve according to any of claims 12 to 17, wherein said drug formulation further comprises a surfactant.
19. A metering valve according to any of Claims 12 to 18, wherein said drug formulation further comprises a polar cosolvent.
20. A metering valve according to either of Claims 12 to 17 wherein said drug formulation further comprises 0.01 to 5% w/w based upon propellant of a polar cosolvent, which formulation is substantially free of surfactant.
21. A metering valve according to either of claims 19 or 20 wherein said polar cosolvent comprises ethanol.
22. A metered dose inhaler comprising a metering valve according to any of claims 1 to 21 and a MDI can.
23. A metered dose inhaler according to claim 22 wherein said metering valve is crimped into said MDI can.
24. A metered dose inhaler according to either of claims 22 and 23 wherein part or all of the internal surfaces of the MDI can are coated with one or more fluorocarbon polymers.
25. A metered dose inhaler according to claim 24 wherein said fluorocarbon polymer is a perfluorocarbon polymer.
26. A metered dose inhaler according to either of claims 24 and 25 wherein said fluorocarbon polymer is selected from the group consisting of PTFE, PFA, FEP and mixtures thereof.
27. A metered dose inhaler according to claim 26 wherein said fluorocarbon polymer is in combination with a non-fluorocarbon polymer selected from the group consisting of polyamideimide, polyethersulphone and mixtures thereof.
28. A metered dose inhaler according to any of claims 23 to 27 wherein said one or more fluorocarbon polymers are applied to the internal surfaces of the MDI can by a curing process.
29. A metered dose inhaler according to any of claims 21 to 28 additionally comprising a channelling device.
30. A metered dose inhaler according to any of claims 21 to 29 wherein the MDI can contains a drug formulation.
31. A metered dose inhaler according to claim 30 wherein said drug formulation comprises fluticasone propionate or a physiologically acceptable solvate thereof in combination with one or more other pharmacologically active agents.
32. A metered dose inhaler according to claim 30 wherein said drug formulation comprises fluticasone propionate or a physiologically acceptable solvate thereof in combination with a bronchodilator or an antiallergic.
33. A metered dose inhaler according to claim 31 wherein said drug formulation comprises fluticasone propionate or a physiologically acceptable solvate thereof in combination with a drug selected from the group comprising salmeterol xinafoate, salbutamol or a physiologically acceptable solvate thereof.
34. Use of a metering valve according to any of claims 1 to 21 for delivering a predetermined amount of drug formulation.
35. Use of a metered dose inhaler according to any of claims 22 to 33 for delivering a predetermined amount of drug formulation.